



## Flammability Ratings of RJR Plastics and Epoxies

| Material Tested                                  | Test Method/Procedure   | Results/Rating                   |
|--|---|----------------------------------|
| Plastic Molding Compound Ingredients             | UL94  | VO with burn Length of 1/32 inch |
| RJR Epoxy  | UL94 not applicable to thin film products                         | *see below                       |
| Plastic Molding Compound Ingredients & RJR Epoxy | D2863 (min % of oxygen required to marginally support combustion) | >40%                             |

\*No significant decomposition or combustion occurs below ~400°C, and the combustion products are typical of natural or synthetic organic compounds. Similar materials like epoxy molding compounds and glass filled PC boards also have VO ratings. There are no halogen or asbestos compounds present in any of our materials.